

TIN (Sn) BASE		PURE TIN																	HIGH PURITY																	DISC/BLOCK			
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
351-192G	%								0.0007	0.0002		0.0005	0.0007		0.0007																								
SnSb		Sb				Others/Set Only	Size	Type	Form			SnSb			Sb						Others/Set Only	Size	Type	Form															
265-TA1	%	1.03					Ø 40x13mm	RM	Disc			265-TA8		%	8.02							Ø 40x13mm	RM	Disc															
265-TA2	%	2.01					Ø 40x13mm	RM	Disc			265-TA10		%	0.09							Ø 40x13mm	RM	Disc															
265-TA3	%	3.05					Ø 40x13mm	RM	Disc			265-TA12		%	2.42							Ø 40x13mm	RM	Disc															
265-TA5	%	5.09					Ø 40x13mm	RM	Disc																														
						PURE TIN						PIG TIN																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-NF54/1	%	0.005	0.005	0.01		0.002	0.002	0.002	0.01	0.005	0.005	0.002	0.03		0.005				0.0005	R		Y	Ø 40x13mm	RM	Disc														
265-NF54/2	%	0.01	0.01	0.07		0.005	0.005	0.005	0.05	0.01	0.01	0.005	0.15		0.01				0.001	R		Y	Ø 40x13mm	RM	Disc														
265-NF54/3	%	0.03	0.03	0.15		0.01	0.001	0.01	0.15	0.015	0.02	0.01	0.4		0.02				0.003	R		Y	Ø 40x13mm	RM	Disc														
265-NF54/4	%	0.06		0.3		0.02	0.005	0.02	0.3	0.025	0.04	0.02	0.7		0.04				0.007	R		Y	Ø 40x13mm	RM	Disc														
265-NF54/5	%	0.1		0.5		0.035	0.01		0.5		0.08		1		0.08				0.015	R		Y	Ø 40x13mm	RM	Disc														
341-SR1D	%	0.009	0.001	0.003	0.003	0.01	0.007		0.009	0.001	0.015	-0.001	0.03		0.021				0.007	R	Te 0.003	Ø 40x10mm	CRM	Disc															
341-SR2D	%	0.029	0.003	0.041	0.008	0.056	0.041		0.054	0.002	0.049	0.0096	0.127		0.063				0.015	R	Te 0.022	Ø 40x10mm	CRM	Disc															
341-SR3E	%	0.007	0.003	0.061	0.003	0.105	0.022		0.101	0.003	0.029	0.0009	0.29		0.14				0.014	R	Te 0.008	Ø 40x10mm	CRM	Disc															
						TIN ALLOY						SnAg																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-TS3X	%	3		0.01		0.05			0.2				0.02		0.2				0.001	R		Y	Ø 40x13mm	RM	Disc														
265-TS4X	%	4		0.02		0.1			0.1				0.05		0.1				0.0025	R		Y	Ø 40x13mm	RM	Disc														
265-TS5X	%	5		0.05		0.25			0.03				0.1		0.05				0.005	R		Y	Ø 40x13mm	RM	Disc														
						TIN ALLOY						SnSb																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-TA4X	%			0.03		0.1	0.015		0.04	0.04			0.1		4				0.015	R		Y	Ø 40x13mm	RM	Disc														
265-TA5X	%			0.02		0.005	<0.005		0.003	0.004			0.025		5					R		Y	Ø 40x13mm	RM	Disc														
265-TA6X	%			0.05		0.25	0.03		0.08	0.08			0.2		6				0.03	R		Y	Ø 40x13mm	RM	Disc														
341-SA4R	%			0.04		0.13	0.003		0.1	0.09			0.1		3.9				0.006	R		Ø 40x15mm	CRM	C Disc															
341-SA5R	%			0.03		0.003	0.019		0.008	0.007			0.035		5.3				0.001	R		Ø 40x15mm	CRM	C Disc															
341-SA6R	%			0.057		0.23	0.009		0.07	0.03			0.22		5.9				0.022	R		Ø 40x15mm	CRM	C Disc															
						TIN ALLOY						SnSbCuPb																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Alloy															
185-LA1	%			0.012		0.014	1.41		2.45	0.012		0.011	3.18		6.79				0.0016	R		Y	Ø40x25mm	CRM															
185-LA2	%		0.092			0.033	0.88		3.84	0.018		0.094	2.17		7.81					R		Y	Ø40x25mm	CRM															
185-LA3	%			0.24		0.059	0.5		8.13	0.059		0.28	1.19		10.22				0.0095	R		Y	Ø40x25mm	CRM															
185-LA4	%			0.43		0.085	0.096		6.35	0.08		0.45	0.41		11.66					R		Y	Ø40x25mm	RM															
185-LA5	%			0.54		0.099	0.011		5.45	0.096		0.53	0.07		13.58				0.021	R		Y	Ø40x25mm	CRM															

TIN (Sn) BASE				TIN ALLOY				SnSbCu										DISC/BLOCK					
	Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn	Others/Set Only	Size	Type	Form	
265-TB/1	%	<0.005	0.001		0.0021	0.0047		3	0.013			0.003		9			0.0006	R		/Y	Ø 40x13mm	RM	Disc
265-TB/2	%		0.029		0.01	0.047		5	0.036			0.029		8			0.002	R		/Y	Ø 40x13mm	RM	Disc
265-TB/3	%		0.105		0.095			6	0.079			0.15		7			0.008	R		/Y	Ø 40x13mm	RM	Disc
265-TB/4	%		0.307		0.2			8.6				0.348		6				R		/Y	Ø 40x13mm	RM	Disc
265-TB/5	%	0.013			0.31	0.098		4	0.055			0.51		4				R		/Y	Ø 40x13mm	RM	Disc
341-SC1	%	0.01	0.0025	0.008	0.084	0.006	<-0.001	2.02	0.0025	0.008	0.0041	0.067	(<-0.002)	1.48			0.003				Ø40x15mm	CRM	C
341-SC2	%	0.006	-0.002	0.035	0.62	0.036	0.021	1.06	0.03	-0.002	0.0048	0.029	(<-0.001)	3.07			0.003				Ø40x15mm	CRM	C
341-SC3	%	0.013	0.001	0.029	0.02	0.024	0.006	0.222	0.017	0.031	0.0136	0.04	-0.002	4.6			0.0014				Ø40x15mm	CRM	C
341-SC4	%	0.042	0.005	0.005	0.218	0.052	0.0035	3.05	0.011	0.011	0.017	0.514	-0.003	6.02			0.008				Ø40x15mm	CRM	C
341-SC5	%	0.063	0.003	0.013	0.43	0.008	0.011	0.57	0.004	0.036	0.0058	0.136	-0.001	7.03			0.001				Ø40x15mm	CRM	C
341-SC6	%	0.08	-0.003	0.204	0.115	0.0125	0.005	5.17	0.007	0.058	0.013	0.1	-0.004	0.092			0.01				Ø40x15mm	CRM	C
341-SC7	%	0.006	0.001	0.047	0.009	0.018	0.016	6.51	0.046	0.014	0.008	0.356	(<-0.001)	14.01			-0.003				Ø40x15mm	CRM	C
341-SC8	%	-0.0015	0.004	0.121	0.037	0.133	0.017	3.89	0.073	0.017	0.014	0.037	-0.011	9.65			0.008				Ø40x15mm	CRM	C
341-SC9	%	0.004	<-0.001	0.53	0.066	0.078	0.003	8.47	0.037	0.01	0.008	0.2	-0.008	8.18			0.003				Ø40x15mm	CRM	C
341-SC11	%	0.06	<-0.002	0.31	0.537	0.065		10.54	0.072		0.49	0.04		11.63			0.065				Ø40x15mm	CRM	C
341-SC12	%	0.83	<-0.002	0.024	0.02	0.02		7.72	0.051		0.384	0.024		8.05			0.02				Ø40x15mm	CRM	C
341-BIS40P1A	%	0.036	0.001	0.005	-56.3	0.013		0.11	0.002	0.054		0.087		0.11			0.014	42.8			Ø40x15mm	RM	C
341-CDSS0P1A	%	0.034	0.001	0.03	0.15	17.9		0.25	0.002	0.093		-31.1		0.12			0.008	49.9			Ø40x15mm	RM	C
				TIN ALLOY				SOLDERS															
	Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn	Others/Set Only	Size	Type	Alloy	
341-E	%	0.73		0.09	0.01	0.002		2.9	0.05		0.01	0.025		0.03	0.001		<-0.001				Ø40x15mm	CRM	C
341-HA	%	2.61		0.008	0.06	0.002		0.6	0.051		0.016	0.023		2.02			2.58				Ø40x15mm	CRM	C
341-HB	%	0.072		0.028	0.007	0.011		4.78	0.11		1.08	0.058		5.05			0.016				Ø40x15mm	CRM	C
341-HN	%	0.15		0.02	0.15	0.003		4	0.01		0.003	0.08		0.02	0.005		0.002				Ø40x15mm	CRM	C
341-TC	%	0.012		0.04	0.04	0.005		5	0.035		0.005	0.17		0.04	0.075		0.005				Ø40x15mm	CRM	C
341-AM	%	0.54		0.065	0.205	0.006		3.05	0.056		0.03	0.18		1.07			0.002				Ø40x15mm	CRM	C
				TIN ALLOY				SETTING-UP SAMPLES (SUS)															
	Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn	Others/Set Only	Size	Type	Form	
084-RSN10	%	<1a	<5a	<10a	<5a	<1a		<5a	<5a	<5a	<5a	<10a	<3a	<10a		<5a	<1a	99.99	P <3a		Ø 40x40mm	SUS	Disc
084-RSN11	%		<0.002		<0.001			<0.003	<0.001			<0.002		<0.003			0.001	99.9			Ø 40x40mm	SUS	Disc
084-RSN12	%	0.2	<0.0005	0.25	0.09	0.1	0.0001	0.95	0.001	0.15	0.002	38		2		0.2	0.015	58			Ø 40x40mm	SUS	Disc
084-RSN13	%	0.0035	0.1	<0.001	0.04	0.015	0.1	0.2	0.2	<0.001	0.15	1		15		0.001	0.015	83			Ø 40x40mm	SUS	Disc
341-SNSUS6	%	0.09	0.015	0.4	0.003	0.09	0.009	0.015	0.4	0.02	0.003	0.015	0.9		0.13		0.003	0.003	Pt 0.003 Pd 0.003		Ø40x40mm	SUS	
341-SNSUS7	%	0.12	0.002	2.5	0.001	2.4	0.015	0.03	11.2	0.3	0.05	0.1	0.3		10.5		0.05	0.01			Ø45x25mm	SUS	

